Acta Crystallographica Section E

Structure Reports

Online

ISSN 1600-5368

Editors: W. Clegg and D. G. Watson

Dibenzimidazo[2,1-*a*:1',2'-*b*]anthra[2,1,9-*def*:6,5,10-*d'e'f'*]diisoquinoline-6,11-dione: *cis* form (II)

Jin Mizuguchi

Copyright © International Union of Crystallography

Author(s) of this paper may load this reprint on their own web site provided that this cover page is retained. Republication of this article or its storage in electronic databases or the like is not permitted without prior permission in writing from the IUCr.

Dibenzimidazo[2,1-*a*:1',2'-*b'*]anthra[2,1,9-*def*:6,5,10-*d'e'f'*]diisoquinoline-6,11-dione: *cis* form (II)

Jin Mizuguchi

Department of Applied Physics, Graduate School of Engineering, Yokohama National University, Tokiwadai 79-5, Hodogaya-ku, Yokohama 240-8501, Japan

Correspondence e-mail: mizu-j@ynu.ac.jp

Key indicators

Single-crystal X-ray study
 $T = 93\text{ K}$
 Mean $\sigma(\text{C}-\text{C}) = 0.007\text{ \AA}$
 Disorder in main residue
 R factor = 0.083
 wR factor = 0.196
 Data-to-parameter ratio = 10.4

For details of how these key indicators were automatically derived from the article, see <http://journals.iucr.org/e>.

The title compound, $\text{C}_{36}\text{H}_{16}\text{N}_4\text{O}_2$, is the *cis* form of a benzimidazole perylene derivative used as a black pigment. The molecule is planar and stacked along the *a* axis. Because of an orientational disorder, a crystallographic center of symmetry appears at the site of the molecule, although the molecule does not have a center of symmetry.

Received 8 March 2005
 Accepted 14 March 2005
 Online 25 March 2005

Comment

Perylene imide compounds are well known organic pigments which exhibit a variety of shades in the range from red *via* maroon to black (Herbst & Hunger, 1993). The title compound, (II), is the *cis* form of a benzimidazoleperylene derivative (abbreviated to BIP) used as a black pigment (Mizuguchi & Shimo, 2005). The background for the present study has been set out in our previous paper (Mizuguchi, 2005), which describes the structure of the *trans* form (I) of BIP.

An *ORTEP* plot (Burnett & Johnson, 1996) of (II) is shown in Fig. 1. The molecule has local C_{2v} symmetry, giving a small dipole moment. The present symmetry is, however, obviously not compatible with the fact that the molecule lies on a center of symmetry. This is due to the orientational disorder of the molecule, as described in the *Experimental* section. The present disordered structure is quite similar to

Figure 1

A view of the molecular structure of (II), showing 50% displacement ellipsoids for non-H atoms. In order to show only one of two possible orientations of the molecule, a set of atoms with 50% site occupancy ($\text{O}2/\text{N}3/\text{C}19\text{--C}23$ and $\text{O}1'/\text{N}2'/\text{C}1'\text{--C}5'$) have been omitted. [Symmetry code: (i) $1 - x, 1 - y, 2 - z$.]

that of the *cis* form of the perinone analog (Mizuguchi, 2003). Fig. 2 shows the projection of the crystal structure along the *a* axis. The molecules are arranged in a zigzag fashion along the *b* axis. Furthermore, the molecules are stacked along the *a* axis.

Experimental

BIP was synthesized by reaction of perylenetetracarboxylic dianhydride with 1,2-phenylenediamine in phenol at 483 K for 6 h (Tamizhmani *et al.*, 1991). The products contained both *trans*-(I) and *cis*-(II) isomers of BIP. The isomers were separated by chromatography using a carrier based on a mixed solvent of trifluoroacetic acid and toluene. The *cis* or *trans* configuration has been confirmed by means of UV-vis solution spectra together with molecular orbital calculations. BIP powders of the *cis* form (II) were purified by sublimation under argon at about 675 K, using a two-zone furnace (Mizuguchi, 1981). Single crystals were then grown from the vapor phase in a closed system at about 650 K. After 48 h, a number of black needle crystals of (II) were obtained.

Crystal data

$C_{36}H_{16}N_4O_2$	$D_x = 1.551 \text{ Mg m}^{-3}$
$M_r = 536.55$	Cu K α radiation
Monoclinic, $P2_1/c$	Cell parameters from 8833 reflections
$a = 4.7501$ (6) Å	$\theta = 3.2\text{--}71.6^\circ$
$b = 28.079$ (3) Å	$\mu = 0.79 \text{ mm}^{-1}$
$c = 8.728$ (1) Å	$T = 93.2 \text{ K}$
$\beta = 99.21$ (1) $^\circ$	Needle, black
$V = 1149.1$ (2) Å 3	$0.50 \times 0.05 \times 0.02 \text{ mm}$
$Z = 2$	

Data collection

Rigaku R-Axis RAPID Imaging Plate diffractometer	1969 independent reflections
ω scans	791 reflections with $F^2 > 2\sigma(F^2)$
Absorption correction: multi-scan (ABSCOR; Higashi, 1995)	$R_{\text{int}} = 0.08$
$T_{\text{min}} = 0.727$, $T_{\text{max}} = 0.984$	$\theta_{\text{max}} = 68.2^\circ$
12407 measured reflections	$h = -4 \rightarrow 4$
	$k = -33 \rightarrow 33$
	$l = -10 \rightarrow 10$

Refinement

Refinement on F^2	H-atom parameters not refined
$R[F^2 > 2\sigma(F^2)] = 0.083$	$w = 1/[\sigma^2(F_o^2) + \{0.05[\text{Max}(F_o^2, 0) + 2F_c^2/3]\}^2]$
$wR(F^2) = 0.196$	$(\Delta/\sigma)_{\text{max}} = 0.009$
$S = 1.14$	$\Delta\rho_{\text{max}} = 0.30 \text{ e \AA}^{-3}$
1963 reflections	$\Delta\rho_{\text{min}} = -0.25 \text{ e \AA}^{-3}$
188 parameters	

Table 1

Selected geometric parameters (Å, $^\circ$).

N1—C6	1.374 (6)	N3—C7	1.119 (9)
N1—C7	1.378 (6)	N3—C23	1.43 (1)
N2—C1	1.35 (1)	C1—C6	1.355 (9)
N2—C18	1.16 (1)	C6—C23	1.34 (1)
C10—C11—C14—C15	−2.8 (6)	C11—C14—C15—C16	−178.6 (4)

Figure 2

Projection of the crystal structure of (II) along the *a* axis. One of two possible orientations of the molecule has been omitted.

The molecule is disordered in the five-membered ring and at the extremity of the perylene imide skeleton, just as in the case of the *cis* form of the perinone analog (Mizuguchi, 2003). Because of this, a crystallographic center of symmetry appears at the site of the molecule, although the molecule is of the *cis* form. It was assumed that the seven rings around the center of the molecule are not disordered, since they possess a center of symmetry. The terminal part has two possible sets of atoms O1/N2/C1—C5 and O2/N3/C19—C23 with 50% occupancy each, except for atom C6 which is shared. The atoms with occupancy factors of 50% were refined isotropically, except for atom O2 which was refined anisotropically. All H atoms on the perylene imide skeleton were positioned geometrically [$C-H = 0.95 \text{ Å}$ and $U_{\text{iso}}(H) = 1.2U_{\text{eq}}(C)$] and not refined. On the other hand, the H atoms attached to the disordered C atoms were also positioned by calculation, but these were shifted slightly during the least-squares refinement, to maintain sensible geometry.

Data collection: *PROCESS-AUTO* (Rigaku, 1998); cell refinement: *PROCESS-AUTO*; data reduction: *TEXSAN* (Molecular Structure Corporation, 2001); program(s) used to solve structure: *SHELXS97* (Sheldrick, 1997); program(s) used to refine structure: *TEXSAN*; molecular graphics: *ORTEPIII* (Burnett & Johnson, 1996); software used to prepare material for publication: *TEXSAN*.

The author thanks Mr I. Suzuki for experimental assistance.

References

- Burnett, M. N. & Johnson, C. K. (1996). *ORTEPIII*. Report ORNL-6895. Oak Ridge National Laboratory, Tennessee, USA.
- Herbst, W. & Hunger, K. (1993). *Industrial Organic Pigments*, pp. 467–475. Weinheim: VCH.
- Higashi, T. (1995). *ABSCOR*. Rigaku Corporation, Tokyo, Japan.
- Mizuguchi, J. (1981). *Cryst. Res. Technol.* **16**, 695–700.
- Mizuguchi, J. (2003). *Z. Kristallogr. New Cryst. Struct.* **218**, 139–140.
- Mizuguchi, J. (2005). *E61*, o1064–o1065.
- Mizuguchi, J. & Shimo, N. (2005). *J. Imaging Sci. Technol.* In the press.
- Molecular Structure Corporation (2001). *TEXSAN*. Version 1.11. MSC, 9009 New Trails Drive, The Woodlands, TX 77381-5209, USA.
- Rigaku (1998). *PROCESS-AUTO*. Rigaku Corporation, Tokyo, Japan.
- Sheldrick, G. M. (1997). *SHELXS97*. University of Göttingen, Germany.
- Tamizhmani, G., Dopelet, J., Côté, R. & Gravel, D. (1991). *Chem. Mater.* **3**, 1046–1053.