Acta Crystallographica Section E

Structure Reports

Online

ISSN 1600-5368

Editors: **W. Clegg** and **D. G. Watson**

5,7,12,14-Tetrahydro[2,3-*b*]quinolinoacridine (β form)

Naoko Nishimura, Takatoshi Senju and Jin Mizuguchi

Copyright © International Union of Crystallography

Author(s) of this paper may load this reprint on their own web site provided that this cover page is retained. Republication of this article or its storage in electronic databases or the like is not permitted without prior permission in writing from the IUCr.

5,7,12,14-Tetrahydro[2,3-*b*]quinolinoacridine (β form)

Naoko Nishimura, Takatoshi Senju and Jin Mizuguchi*

Department of Applied Physics, Graduate School of Engineering, Yokohama National University, Tokiwadai 79-5, Hodogaya-ku, Yokohama 240-8501, Japan

Correspondence e-mail: mizu-j@ynu.ac.jp

Key indicators

Single-crystal X-ray study

 $T = 296$ KMean $\sigma(\text{C}-\text{C}) = 0.009$ Å R factor = 0.160 wR factor = 0.431

Data-to-parameter ratio = 10.8

For details of how these key indicators were automatically derived from the article, see <http://journals.iucr.org/e>.

The title compound, $\text{C}_{20}\text{H}_{12}\text{N}_2\text{O}_2$, is a centrosymmetric pigment molecule. The molecules are doubly linked *via* $\text{N}-\text{H}\cdots\text{O}$ hydrogen bonds, forming ribbons along $[110]$ and $[1\bar{1}0]$.

Comment

The title compound, commonly known as quinacridone (QA), (I), is an industrially important red pigment (Herbst & Hunger, 1997). As early as 1958, three crystal modifications of QA (α , β and γ forms) were known to exist as powders, of which only the β and γ forms are of commercial value. The structure analyses of QA derivatives based on single crystals were reported recently for dithio-QA (Mizuguchi & Rihs, 1992) and for γ -QA (Potts *et al.*, 1994; Mizuguchi *et al.*, 2002). The γ form is typically characterized by a three-dimensional $\text{N}-\text{H}\cdots\text{O}$ hydrogen-bond network, where one molecule is hydrogen-bonded to four neighbouring molecules. As for the β form, Paulus *et al.* (1989) published the lattice parameters, but details of the molecular arrangement remained unknown.

We report here the structure of the β form of QA based on single crystals grown from the vapour phase. The key factor for the successful growth of the β form was found in the course of our investigation of the QA latent pigment (a precursor of QA), from which QA can be thermally regenerated around 473 K (Imura *et al.*, 2005). We noticed that the regenerated crystals were always of the β form, whereas the γ form was obtained at a higher temperature of around 623 K (Mizuguchi, Sasaki *et al.*, 2002). Therefore, we firmly believed that the β form could be grown at a condensation temperature of about 473–523 K. In fact, this condition led us to the successful growth of the β form from a purified sample of QA. The lattice parameters of the present investigation are in fairly good agreement with those of Paulus *et al.* (1989).

An *ORTEP*III (Burnett & Johnson, 1996) plot of (I) is shown in Fig. 1. The molecule has C_i symmetry, but it is not entirely planar. The dihedral angles between the planes *A* ($\text{C}1-\text{C}5/\text{C}9$) and *B* ($\text{C}5/\text{N}1/\text{C}6-\text{C}9$), *A* and *C* [$\text{C}6/\text{C}7/\text{C}10/\text{C}6^i/\text{C}7^i/\text{C}10$; symmetry code (i) $-x, 2-y, -z$], and *B* and *C* are 2.1 (2), 1.8 (2), and 0.5 (2)°, respectively.

Figure 1
A view of the molecular structure of (I), showing 50% probability displacement ellipsoids. Unlabelled atoms are related to labelled atoms by the symmetry operation $(-x, 2 - y, -z)$.

Figure 2
The packing arrangement in (I). H atoms have been omitted unless these are involved in hydrogen bonds (dashed lines).

Fig. 2 shows the packing arrangement of (I) in the crystal structure. There are intermolecular $N-H \cdots O$ hydrogen bonds (Table 1) between the QA molecules, forming ribbons along $[110]$ and $[1\bar{1}0]$. One QA molecule is bonded to two neighbouring molecules through four $N-H \cdots O$ hydrogen bonds with a small step of *ca* 0.53 Å between the hydrogen-bonded molecular planes. The QA molecules are stacked along the *b* axis.

Experimental

QA was obtained from CIBA Specialty Chemicals and purified three times by sublimation under vacuum using a two-zone furnace (Mizuguchi, 1981). Single crystals were then grown from the vapour

phase in a closed system at sublimation and condensation temperatures of 623 and 473 K, respectively. A number of tiny platelet crystals were obtained over a period of 72 h.

Crystal data

$C_{20}H_{12}N_2O_2$
 $M_r = 312.32$
Monoclinic, $P2_1/c$
 $a = 5.7366$ (6) Å
 $b = 3.8851$ (4) Å
 $c = 29.880$ (4) Å
 $\beta = 95.861$ (8) $^\circ$
 $V = 662.46$ (13) Å 3

$Z = 2$
 $D_x = 1.566$ Mg m $^{-3}$
Cu $K\alpha$ radiation
 $\mu = 0.83$ mm $^{-1}$
 $T = 296.1$ K
Platelet, red
 $0.42 \times 0.20 \times 0.04$ mm

Data collection

Rigaku R-Axis RAPID
diffractometer
 ω scans
Absorption correction: multi-scan
(*ABSCOR*; Higashi, 1995)
 $T_{\min} = 0.705$, $T_{\max} = 0.965$

5102 measured reflections
1187 independent reflections
977 reflections with $F^2 > 2\sigma(F^2)$
 $R_{\text{int}} = 0.120$
 $\theta_{\max} = 68.3^\circ$

Refinement

Refinement on F^2
 $R[F^2 > 2\sigma(F^2)] = 0.160$
 $wR(F^2) = 0.431$
 $S = 1.06$
1187 reflections
110 parameters
H-atom parameters constrained

$w = 1/[\sigma^2(F_o^2) + (0.1985P)^2 + 9.1P]$
where $P = (F_o^2 + 2F_c^2)/3$
 $(\Delta/\sigma)_{\max} < 0.001$
 $\Delta\rho_{\max} = 2.40$ e Å $^{-3}$
 $\Delta\rho_{\min} = -0.48$ e Å $^{-3}$

Table 1

Hydrogen-bond geometry (Å, $^\circ$).

$D-H \cdots A$	$D-H$	$H \cdots A$	$D \cdots A$	$D-H \cdots A$
$N1-H1N \cdots O1^{ii}$	0.86	2.02	2.848 (8)	161

Symmetry code: (ii) $x + 1, y + 1, z$.

All H atoms were placed in geometrically idealized positions and constrained to ride on their parent atoms, with $C-H = 0.93$ and $N-H = 0.86$ Å, and with $U_{\text{iso}}(H) = 1.2U_{\text{eq}}(\text{parent atom})$. The highest residual density peak is located 1.51 Å from atom O1. The U_{eq} of O1 is larger than those of the other non-H atoms. This might be due to the extremely small size of the crystal and also its poor crystallinity.

Data collection: *PROCESS-AUTO* (Rigaku, 1998); cell refinement: *PROCESS-AUTO*; data reduction: *CrystalStructure* (Rigaku/MS, 2005); program(s) used to solve structure: *SIR2002* (Burla *et al.*, 2003); program(s) used to refine structure: *SHELXL97* (Sheldrick, 1997); molecular graphics: *ORTEP III* (Burnett & Johnson, 1996); software used to prepare material for publication: *CrystalStructure*.

References

- Burla, M. C., Camalli, M., Carrozzini, B., Cascarano, G. L., Giacovazzo, C., Polidori, G. & Spagna, R. (2003). *J. Appl. Cryst.* **36**, 1103.
- Burnett, M. N. & Johnson, C. K. (1996). *ORTEP III*. Report ORNL-6895. Oak Ridge National Laboratory, Tennessee, USA.
- Herbst, W. & Hunger, K. (1997). *Industrial Organic Pigments*, 2nd ed., pp. 454–474. Weinheim: VCH.
- Higashi, T. (1995). *ABSCOR*. Rigaku Corporation, Tokyo, Japan.
- Imura, Y., Yamashita, Y., Senju, T. & Mizuguchi, J. (2005). *J. Imag. Sci. Jpn.*, **44**, 138–142.
- Mizuguchi, J. (1981). *Kristallogr. Technol.* **16**, 695–700.

- Mizuguchi, J. & Rihs, G. (1992). *Acta Cryst.* **C48**, 1553–1555.
- Mizuguchi, J., Sasaki, T. & Tojo, K. (2002). *Z. Kristallogr. New Cryst. Struct.* **217**, 249–250.
- Paulus, E. F., Dietz, E., Kroh, A., Prokschy, F. & Lincke, G. (1989). *XII European Crystallographic Meeting Collected Abstracts*, Vol. 2, pp. 23–24. Moscow: Viniti.
- Potts, G. D., Jones, W., Bullock, J. F., Andrews, S. J. & Maginn, S. J. (1994). *J. Chem. Soc. Chem. Commun.* pp. 2565–2566.
- Rigaku (1998). *PROCESS-AUTO*. Rigaku Corporation, Tokyo, Japan.
- Rigaku/MS (2005). *CrystalStructure*. Version 3.7.0. Rigaku/MS Inc., The Woodlands, Texas, USA.
- Sheldrick, G. M. (1997). *SHELXL97*. University of Göttingen, Germany.