Acta Crystallographica Section E

Structure Reports

Online

ISSN 1600-5368

Editors: W. Clegg and D. G. Watson

Ammonium bis{3-anilinocarbonyl-1-[(5-chloro-2-oxidophenyl)diazenyl]-2-naphtholato}ferrate(III) acetone solvate

Jin Mizuguchi, Kazuya Uta and Yohei Sato

Copyright © International Union of Crystallography

Author(s) of this paper may load this reprint on their own web site provided that this cover page is retained. Republication of this article or its storage in electronic databases or the like is not permitted without prior permission in writing from the IUCr.

Ammonium bis[3-anilinocarbonyl-1-[(5-chloro-2-oxidophenyl)diazenyl]-2-naphtholato]ferrate(III) acetone solvate

Jin Mizuguchi,* Kazuya Uta and Yohei Sato

Department of Applied Physics, Graduate School of Engineering, Yokohama National University, Tokiwadai 79-5, Hodogaya-ku, Yokohama 240-8501, Japan

Correspondence e-mail: mizu-j@ynu.ac.jp

Key indicators

Single-crystal X-ray study

$T = 100\text{ K}$

Mean $\sigma(\text{C}-\text{C}) = 0.008\text{ \AA}$

R factor = 0.089

wR factor = 0.257

Data-to-parameter ratio = 13.8

For details of how these key indicators were automatically derived from the article, see <http://journals.iucr.org/e>.

The title compound, $(\text{NH}_4)[\text{Fe}(\text{C}_{23}\text{H}_{24}\text{ClN}_3\text{O}_3)_2] \cdot \text{C}_3\text{H}_6\text{O}$, is a charge-control agent used in electrophotography. The central Fe^{III} atom is coordinated by four O atoms and two N atoms of two symmetry-independent ligands. The metallic complex has no crystallographic symmetry.

Received 25 February 2007

Accepted 3 April 2007

Comment

This paper reports a structural study of the title compound, (I). For the background to this study see the preceding paper (Mizuguchi *et al.*, 2007), which describes the structure of the methanol-solvated complex.

Fig. 1 shows the molecular structure of (I). The network of hydrogen bonds that links the metallic complexes is different from that reported in the preceding paper. In (I) the ammonium ion shares its H atoms with the O atoms of three different complexes (Table 1) and the solvent molecule, while in the methanol-solvated structure, the ammonium ion shares its H atoms with two metal complexes and the solvent molecule. Interestingly the ions are again assembled in chains that run along the a axis.

Experimental

Compound (I) was prepared as described by Mizuguchi *et al.* (2007) and recrystallized from an acetone solution.

Crystal data

$(\text{NH}_4\text{N})[\text{Fe}(\text{C}_{23}\text{H}_{24}\text{ClN}_3\text{O}_3)_2] \cdot \text{C}_3\text{H}_6\text{O}$

$M_r = 963.61$

Monoclinic, $P2_1/n$

$a = 11.3199(14)\text{ \AA}$

$b = 13.7962(17)\text{ \AA}$

$c = 27.757(4)\text{ \AA}$

$\beta = 93.747(3)^\circ$

$V = 4325.6(10)\text{ \AA}^3$

$Z = 4$

Mo $K\alpha$ radiation

$\mu = 0.54\text{ mm}^{-1}$

$T = 100\text{ K}$

$0.10 \times 0.10 \times 0.04\text{ mm}$

Figure 1
The molecular structure of (I), showing 50% probability displacement ellipsoids.

Data collection

Rigaku R-Axis RAPID
diffractometer
Absorption correction: multi-scan
(*ABSCOR*; Higashi, 1995)
 $T_{\min} = 0.950$, $T_{\max} = 0.979$
53581 measured reflections
8466 independent reflections
4761 reflections with $F^2 > 2\sigma(F^2)$
 $R_{\text{int}} = 0.196$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.089$
 $wR(F^2) = 0.257$
 $S = 1.00$
8466 reflections
612 parameters
H atoms treated by a mixture of
independent and constrained
refinement
 $\Delta\rho_{\max} = 0.98 \text{ e } \text{\AA}^{-3}$
 $\Delta\rho_{\min} = -0.61 \text{ e } \text{\AA}^{-3}$

Table 1

Hydrogen-bond geometry ($\text{\AA}$, $^\circ$).

$D-H\cdots A$	$D-H$	$H\cdots A$	$D\cdots A$	$D-H\cdots A$
$N5-H5N\cdots O4$	0.88	1.99	2.675 (5)	134
$N6-H6N\cdots O3$	0.88	1.98	2.661 (6)	133
$N7-H1A\cdots O7$	0.70 (7)	2.28 (6)	2.860 (8)	140 (6)
$N7-H1B\cdots O5^i$	1.00 (7)	2.06 (7)	2.791 (7)	128 (5)
$N7-H1C\cdots O6^{ii}$	0.98 (8)	1.87 (8)	2.797 (7)	156 (7)
$N7-H1D\cdots O1$	1.01 (6)	1.80 (6)	2.800 (7)	172 (5)

Symmetry codes: (i) $x - 1, y, z$; (ii) $-x, -y + 1, -z + 1$.

Figure 2
The packing of (I) showing the chain formation through hydrogen bonding. H atoms not involved in hydrogen bonding have been omitted for clarity.

The four H atoms of the ammonium cation were found in difference maps and their parameters were refined. All remaining H atoms were placed in geometrically idealized positions and constrained to ride on their parent atoms, with $C-H = 0.95$ and $0.98 \text{ \AA}$, $N-H = 0.88 \text{ \AA}$, and $U_{\text{iso}}(H) = 1.2U_{\text{eq}}(\text{parent atom})$. Although the data collection was performed at 100 K, R_{int} was found to be rather poor (0.196).

Data collection: *PROCESS-AUTO* (Rigaku, 1998); cell refinement: *PROCESS-AUTO*; data reduction: *CrystalStructure* (Rigaku/MS, 2006); program(s) used to solve structure: *SIR2004* (Burla *et al.*, 2003); program(s) used to refine structure: *SHELXL97* (Sheldrick, 1997); molecular graphics: *ORTEP-III* (Burnett & Johnson, 1996); software used to prepare material for publication: *CrystalStructure*.

References

- Burla, M. C., Camalli, M., Carrozzini, B., Cascarano, G. L., Giacovazzo, C., Polidori, G. & Spagna, R. (2003). *J. Appl. Cryst.* **36**, 1103.
Burnett, M. N. & Johnson, C. K. (1996). *ORTEP-III*. Report ORNL-6895. Oak Ridge National Laboratory, Tennessee, USA.
Higashi, T. (1995). *ABSCOR*. Rigaku Corporation, Tokyo, Japan.
Mizuguchi, J., Sato, Y. & Uta, K. (2007). *Acta Cryst. E* **63**, m1327–m1328.
Rigaku (1998). *PROCESS-AUTO*. Rigaku Corporation, Tokyo, Japan.
Rigaku/MS (2006). *CrystalStructure*. Version 3.8.1. Rigaku/MS, The Woodlands, Texas, USA.
Sheldrick, G. M. (1997). *SHELXL97*. University of Göttingen, Germany.